

CLAIMS

1. A free flowing dry back-up insulating material comprising :

- 5
- from 67 to 96% by weight of fly-ash;
 - from 2 to 15% by weight of a heat sensitive binder;
 - from 2 to 7% by weight of a non-wetting agent;
 - from 0 to 10% by weight of a heat expandable material;
- and
- 10
- from 0 to 1% by weight of a dust suppressant.

2. The material for claim 1, wherein:

- 15
- the fly ash consists of cenospheres;
 - the heat sensitive binder is selected from the group consisting of boric acid and anhydrous boron oxide;
 - the non-wetting agent is selected from the group consisting of calcium fluoride, magnesium fluoride and barium sulfate;
 - the heat expandable material is selected from the group consisting of vermiculite and graphite; and
- 20
- the dust suppressant is selected from the group consisting of kerosene, mineral oils and vegetable oils.

3. The material of claim 1, wherein said material comprises:

- 25
- from about 89.5% to 90% by weight of said fly ash;
 - about 8% by weight of said heat sensitive binder;
 - about 2% by weight of said non-wetting agent; and
 - from about 0 to 0.5% by weight of said dust suppressant.
- 30

4. The material of claim 2, wherein said material comprises:

- from about 89.5% to 90% by weight of said fly ash;
- about 8% by weight of said heat sensitive binder;
- about 2% by weight of said non-wetting agent; and
- from about 0 to 0.5% by weight of said dust suppressant.